

GROUND GYPSUM SUPERFINE WHITE

Construction Materials, Dental and personal care, Food, Agriculture and Environment



PRODUCT DESCRIPTION

Ground Gypsum Superfine White is an extremely high purity, micronised gypsum grade, obtained from naturally occurring mineral. This product is used as a food additive (E516), food processing aid. It is used as an additive for accelerator of setting time or filler in tile adhesive and crack filler formulations, as a filler in polymers and other compounds as an extender in paints, in the formulation of oilwell drilling muds or as a formulant in fire retardant loft insulation and sacrificial anodes. It can also be used as an absorbent and as a carrier for insecticides or in fertilizers for Agriculture and Environment applications

PRODUCT BENEFITS

- + Very High Purity Natural Gypsum
- + Food additive (E516)
- + Fine Particle Size

APPLICATIONS

Floor, Cosmetics, Food and Beverage

TECHNICAL INFORMATION

Chemical Properties	
Chemical Name	Calcium sulphate dihydrate
Minimum gypsum purity %	99
Water of crystallization %	Maximum 23
Moisture Content %	0% at manufacture
Solubility of gypsum in water g / litre	2.1
pH	7
Chemical Composition	CaSO ₄ .2H ₂ O
Physical Properties	
Colour	white
Colorometer L* value	92.5
Colorometer a* value	0.25
Colorometer b* value	3
Mean particle diameter (microns)	20
Seive Analysis (Mesh size and % weight retained)	2.5% at 150 µm 10% at 75 µm
Specific gravity of gypsum	2.32
Apparent Density (g/cm ³)	0.9
Bulk density (loose) kg / m ³	900
Bulk density (compacted) kg / m ³	1200
Gypsum Hardness (MOH scale)	2

The technical data outlined represents typical figures only. For further details, please contact Saint-Gobain Formula directly.

INSTRUCTIONS FOR USE

This product is manufactured from a naturally occurring mineral and therefore variations in colour and non-gypsum content are to be expected.

Microbiological Activity: Ground Gypsum Superfine White a dry powder and an inorganic mineral. Testing is not performed. Appropriate precautions should be taken when the product is employed in the manufacture of food.

Physical Hazards:

- + HACCP critical control points - 25Kg paper sacks
- + Non-Metallic: 3.15mm screen after grinding
- + Metallic: Tunnel metal detection - calibrated to 2.5mm Fe, 3.00mm Stainless steel, 3.0mm non-ferrous

Application Performance: Since the conditions under which Ground Gypsum Superfine White is used are varied and beyond our control, performance is not guaranteed for any particular application.

PACKAGING AND SHELF LIFE

	Packaging Available	Shelf Life (Month)
Bag	25 kg	24
Bulk Bag	1 T	24
Bulk Tanker	< 30 T	Technical properties noted are at receipt of goods

When stored under dry conditions and in its original packaging, the product will have a specified shelf life that commences from the date of manufacture that is displayed on each sack. Shelf life depends on the packaging type. For those products where a defined 'best before' date is applicable, BBE (Best Before End) followed by the date will be displayed on each sack.

CERTIFICATION

Ground Gypsum Superfine White conforms to the specification for E516 Calcium Sulphate Dihydrate, as detailed below, in accordance with Commission Regulation (EU) No 231/2012 laying down specifications for food additives listed in Annexe II and III to Regulation (EC) No 1333/2008

- + Chemical name: Calcium Sulphate
- + EC Additive Number: E516
- + EINECS: 231-900-3
- + Assay: Minimum 99.0%
- + Loss on drying: Maximum 23%
- + Fluoride: 30 mg/Kg max
- + Selenium: 30 mg/Kg max
- + Arsenic: 3 mg/Kg max
- + Lead: 2 mg/Kg max
- + Mercury: 1 mg/Kg max

ENVIRONMENT, HEALTH AND SAFETY

Material Safety Data Sheets of Saint-Gobain Formula plasters and gypsum minerals are available for all products and may be obtained directly on our website in the product and documentation sections. No liability is accepted by Saint-Gobain Formula for injury to any person or loss or damage to property by improper use of the product.

STORAGE

Plaster based products are not recommended for conditions where they are likely to be located externally or in any way subjected to weathering or excessive dampness.

Absorption of moisture can result in changes to physical properties, including a reduction in the set strength of plasters and also a lengthening of setting time.

Gypsum minerals can be affected by absorption of moisture and may change physical properties.

To help protect the product during use, open or part used bags should be carefully folded and closed. Each bag is date stamped and stocks should be rotated so that the oldest material is used first.

NOTIFICATION

The plaster to water ratios quoted are those used in Saint-Gobain Formula's standard test methods and are not necessarily those used in practice. The precise consistency to use will need to be adjusted to suit the individual application. Changes to plaster to water ratio will influence product performance, particularly setting time and strength. Unless otherwise stated, Saint-Gobain Formula's standard test methods apply. To obtain a copy of the test method, please contact Saint-Gobain Formula directly. This literature cancels and replaces any previous document. All information given is provided in good faith and may be subject to change. It's advisable to contact Saint-Gobain Formula in case of any doubt arising from the content of such information.

CONTACT

*For any information, please visit our website
www.saintgobainformula.com*



Sales contact



Documentation



Technical information



Global information